




# indiactiv<sup>®</sup>

R E D

## Indiactiv 'HE'

For hot exhaust economical dyes for standard requirements

Indiactiv "HE"	General Properties			Fastness Properties				Suitability			
	Affinity	Solubility at 30°C	Dischargability	Day Light 1/1 & 1/6	Perspiration			Hypochlorite Bleach	Exhaust at R.T.	Printing	
					Washing ISO4	Alkaline	Acidic			Steam	Silicate
Red HE3B Red 120	H	80	P	4 5	5	4-5	4	3	4	S	NS
Red HE7B Red 141	H	80	P	3-4 4-5	4	4-5	4	3	4-5	S	FS
Red HE8B Red 152	H	80	P	3-4	4	4	4-5	2	4-5	FS	NS



WHERE COLORS & CHEMISTRY, COEXIST.

